

**SELF-ADHERED WATER PROTECTION UV
ACRYLIC WINDOW & DOOR FLASHING**



Meets AAMA 711
 - Adhesion Rating Type A (no primer)
 - Thermal Exposure (Class 3, 80°C)

For proper installation consult the manufacturer instructions or ASTM E2112 for Flashing Exterior Windows and Doors

DESCRIPTION

EvoFlash is made of a multi-layered UV protected film coated with a permanent bond UV cured adhesive. The EvoFlash provides maximum protection against water and moisture penetration around windows and doors.

MAIN FEATURES

- Seals around fasteners and nails (ASTM D1970 section 7.9)
- High shear adhesive provides excellent initial tack to surfaces
- Strong and durable holding power
- Film is flexible and conforms well around surfaces
- Water and moisture resistant
- Prevents air infiltration
- Up to 12 months UV resistance

APPLICATIONS

- Waterproof flashing membrane used to seal openings around windows & doors
- Recommended on aluminum, wood, wood clad, fiberglass, vinyl windows and doors. As well as most building wraps, OBS, exterior gypsum and fibre board.
- All above surfaces have to be dry and clean in order to assure proper contact

TECHNICAL DATA

Color.....	Blue film with white print
Facing.....	Multi-layered UV resistive polyethylene film (PE)
Release Liner.....	Polycoated kraft split liner
Tape Thickness (without liner).....	9.2 mil
ASTM D3652	
Adhesion to	100 oz/in (Steel)
AAMA 711 section 5.3-5.6	100 oz/in (Backing)
ASTM D3330	80 oz/in (Palisade™ House Wrap)
	50 oz/in (Tyvek®)
	91 oz/in (OSB)
	111 oz/in (Anodized Aluminum)
	82 oz/in (Plywood)
	106 oz/in (Vinyl)
	35 oz/in (Polyethylene Vapour Barrier)
Tensile Strength at Break	14 lb/in
ASTM D1970 section 7.3	
Elongation at Break	650%
ASTM D1970 section 7.3	
Nail Sealability.....	Pass (Initial Observation)
ASTM D1970 section 7.9	Pass (After thermal cycling)
TVOC (Total Organic Compound).....	4.09178 • 10 ¹¹ oz/oz product
Air Permeance.....	0.002 cfm/ft ² @ 1.57 psf
ASTM E2178-13	
Water Vapor Resistance	>24 hours
ASTM D779 - Procedure B	
Application Temperature	14°F to 122°F
Service Temperature	- 40°F to 176°F

Please note:

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness.

The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded.

No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.